









JAMAICA HD

915198



Flexible layflat NBR hose with polyester yarn reinforcement, resistant to elongation, for pressurized delivery of liquids and oils.

DETAILS

 SMOOTH SURFACE	* * * * *
 FLEXIBILITY	*
 ABRASION RESISTANCE	* * *
 TEMPERATURE RANGE	-15 °C 80 °C
 CHEMICAL RESISTANCE	NBR
 CRUSHING RESISTANCE	*

Ø nominal mm	Ø i.d. mm	Ø o.d. mm	working pressure at 23 °C bar	bursting press. at 23 °C bar	total thickness mm	weight meter g/m	tensile breaking load kg	Availability
20	20	30	90	90	min. 2.2	215	1200	On demand
22	22	30	90	90	min. 2.2	230	1200	On demand
25	25	30	90	90	min. 2.1	245	1350	On demand
27	27	30	90	90	min. 2.1	260	1350	On demand
32	32	27	80	80	min. 2.0	310	1900	On demand
38	38	21	62	62	min. 2.1	375	2200	On demand
42	42	21	62	62	min. 2.1	395	2400	On demand
45	45	21	62	62	min. 2.1	395	3300	On demand
52	52	17	52	52	min. 2.0	470	4300	On demand
55	55	17	52	52	min. 2.0	470	4450	On demand
63	63	17	52	52	min. 2.2	600	5100	On demand
70	70	17	50	50	min. 2.2	650	6500	On demand
75	75	17	50	50	min. 2.2	710	7000	On demand
78	78	17	50	50	min. 2.2	710	7200	On demand
80	80	15	45	45	min. 2.2	760	7600	On demand
90	90	15	45	45	min. 2.3	930	9200	On demand
102	102	15	45	45	min. 2.4	1000	10500	On demand
104	104	15	45	45	min.2.4	1080	10500	On demand
110	110	13	40	40	min. 2.4	1100	11000	On demand
115	115	13	35	35	min. 2.4	1180	11500	On demand
125	125	15	45	45	min. 2.8	1450	14000	On demand
150	150	13	35	35	min. 2.7	1700	16500	On demand
156	156	13	35	35	min. 2.7	1700	16500	On demand
204	204	12	35	35	min. 3.5	3000	20300	On demand
254	254	10	28	28	min.3.5	3500	24100	On demand
304	304	10	26	26	min. 3.5	3700	30300	On demand

All technical specifications apply to a temperature of 23° C ± 2° C (ISO 291)

The tolerance on all specifications ±5% (Tolerance Percentage is applicable on ALL DATA across our range)